## Amendments to the Claims

This listing of claims replaces all prior versions, and listings, of claims in the application.

## Listing of claims:

- 1. (Original) A sealing material for liquid crystals produced by homogeneously dispersing fine particles (D) having an average particle size of not more than 3  $\mu\text{m}$  in a reactive resin (C) having an epoxy group and/or a (meth)acryloyl group dissolved in a solvent (B) using a wet dispersion unit (A) in which a dispersion vessel (a) contains media (b) as dispersing media and a rapidly rotating stirrer (c) disperses agglomerated particles by allowing the media to collide each other in a high-speed rotating field; and then removing the solvent (B).
- 2. (Original) The sealing material for liquid crystals according to claim 1, wherein the wet dispersion unit (A) is of a continuous processing system.
- 3. (Original) The sealing material for liquid crystals according to claim 1 or 2, wherein said media (b) has a diameter of 0.1 to 5 mm each, and is made of any material selected from alumina, zirconia, zirconia-reinforced alumina, and silicon nitride.
- 4. (Currently amended) The sealing material for liquid crystals according to any of claims 1 to 3 claim 1 or 2, wherein the fine particles (D) has an average particle size of not more than 0.3  $\mu\text{m}$ .

- 5. (Currently amended) The sealing material for liquid crystals according to any of claims 1 to 4 claim 1 or 2, wherein the fine particles (D) are inorganic fine particles (D-1).
- 6. (Original) The sealing material for liquid crystals according to claim 5, wherein the inorganic fine particles (D-1) are made of silica and/or alumina and/or titanium black pigment.
- 7. (Currently amended) The sealing material for liquid crystals according to any of claims 1 to 6 claim 1 or 2, wherein the fine particles (D) are organic fine particles (D-2).
- 8. (Original) The sealing material for liquid crystals according to claim 7, wherein the organic fine particles (D-2) are cross-linked rubber fine particles.
- 9. (Original) The sealing material for liquid crystals according to claim 8, wherein the cross-linked rubber fine particles are cross-linked rubber fine particles having a coreshell structure.
- 10. (Currently amended) The sealing material for liquid crystals according to any of claims 1 to 9 claim 1 or 2, which is obtained by further adding any one or more of additives selected from the group consisting of a curing agent, a curing promoter, a photopolymerization initiator, a polymerization inhibitor, a coupling agent, an ion scavenger, and an antioxidant, and then dispersing, and/or adding one or more of said additives after removing the solvent (B).
- 11. (Withdrawn) A method for producing a sealing material for liquid crystals, characterized by comprising homogeneously dispersing fine particles (D) having an average particle size of

not more than 3  $\mu\text{m}$  in a reactive resin (C) having an epoxy group and/or a (meth)acryloyl group dissolved in a solvent (B) using a wet dispersion unit (A) in which a dispersion vessel (a) contains media (b) as dispersing media and a rapidly rotating stirrer (c) disperses agglomerated particles by allowing the media to collide each other in a high-speed rotating field; and then removing the solvent (B).

- 12. (Currently amended) A liquid crystal display cell sealed with a cured product of the sealing material for liquid crystals according to any of claims 1 to 10 claim 1 or 2.
- 13. (Withdrawn) A method for producing a liquid crystal display cell composed of two substrates, characterized by comprising adding a liquid crystal dropwise inside the weir of the sealing material for liquid crystals according to any of claims 1 to 10 formed on one substrate, bonding the other substrate, and then curing the sealing material by light and/or heat.
- 14. (Withdrawn) A method for producing a liquid crystal display cell composed of two substrates, characterized by comprising bonding two substrates with the sealing material for liquid crystals according to any of claims 1 to 10, curing the sealing material by light and/or heat to form a cell, injecting a liquid crystal, and then sealing an injecting port with an end sealing material.